

PRODUCT DATA SHEET

SikaFiber®-800 Stealth

MACRO SYNTHETIC FIBER

PRODUCT DESCRIPTION

SikaFiber®-800 Stealth is macro synthetic reinforcing fiber. SikaFiber®-800 Stealth is 100% virgin copolymer fiber designed to provide a uniform three dimensional reinforcement system in the concrete mix. The fiber has a patent pending. Specifically engineered and manufactured in an ISO 9001 certified manufacturing facility.

USES

SikaFiber®-800 Stealth can be successfully used as a safe and simple alternative to wire mesh and rebar. Due to its mechanical properties and its outstanding finishability SikaFiber®-800 Stealth is recommended for use in following applications:

- Commercial Slab on ground
- Industrial Slab on ground
- Exposed concrete
- Overlays

CHARACTERISTICS / ADVANTAGES

- Engineered characteristics to create an outstanding finished hard troweled slab on ground
- Geometrically engineered to resist matrix pullout
- Increase in flexural toughness
- Increases cohesion and reduces segregation
- Increases impact and shatter resistance
- Reduced wear on concrete pumps and hoses
- Safe and easy to handle
- Simplified logistics
- Optimized balance between high aspect ratio, performance and finishing.
- Economical alternative to steel wire mesh and/or steel fibers.
- Reducing embodied carbon through the replacement of convention steel reinforcement with synthetic structural fibers.

APPROVALS / STANDARDS

Complies with ASTM C 1116/C1116M Type III Fiber Reinforced Concrete and ASTM D7508 / D7508M

PRODUCT INFORMATION

Chemical Base	Polyolefin
Packaging	SikaFiber®-800 Stealth are pucked and placed various sizes of "toss-in" degradable bags. The bags are packed into cartons and palletized.
Appearance / Color	Grey color, crimped self-fibrillating monofilament macro synthetic fiber
Shelf Life	If stored in dry conditions shelf life is 5 years.
Storage Conditions	SikaFiber®-800 Stealth should be stored in a cool dry warehouse. Protect product from the rain and direct sunlight.
Density	0.91

Dimensions Length: 1.5" (38 mm)

Melting Point 324 °F (162 °C)

TECHNICAL INFORMATION

Resistance to Alkalinity High

APPLICATION INFORMATION

Recommended Dosage The dosage of the SikaFiber®-800 Stealth will vary according to the type of application and the performance requirements of the project. Standard recommended dosage rate of SikaFiber®-800 Stealth is between 3–7 lbs/cu. yd. (1.8–4.15 kg/m³) of concrete. Dosages outside the recommended dosage range can be used to meet project specific requirements. If this is the case please contact your Sika representative for technical support.

Mixing SikaFiber®-800 Stealth in a dispersible bag can be added directly to the concrete mixing system after the batching of the ingredients and mixed for 4 to 5 minutes or 70 revolutions. The addition of SikaFiber®-800 Stealth at the recommended dosage rates may decrease the slump; however, additional water should not be added. Only a water reducing or high range water reducing admixture should be used to adjust concrete to the desired workability.

Application

The addition of SikaFiber®-800 Stealth at the normal recommended dosage rate does not require any mix design or application changes. The fiber concrete can be mixed, sprayed or placed using conventional equipment.

Tooling & Finishing

SikaFiber®-800 Stealth can be used in power/hand troweled concrete and broom finished concrete. Fiber reinforced concrete can be finished by most finishing techniques as indicated in ACI-302. Proper timing and workmanship are important when using a macro synthetic fiber to insure fiber is not elevated at the surface.

BASIS OF PRODUCT DATA

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

toxicological and other safety related data. User must read the current actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

ENVIRONMENTAL, HEALTH AND SAFETY

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data Sheets containing physical, environmental,

OTHER RESTRICTIONS

See Legal Disclaimer.

LEGAL DISCLAIMER

- KEEP CONTAINER TIGHTLY CLOSED
- KEEP OUT OF REACH OF CHILDREN
- NOT FOR INTERNAL CONSUMPTION
- FOR INDUSTRIAL USE ONLY
- FOR PROFESSIONAL USE ONLY

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates (“SIKA”), the user must always read and follow the warnings and instructions on the product’s most current product label, Product Data Sheet and Safety Data Sheet which are available at usa.sika.com or by calling SIKA’s Technical Service Department at 1-800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product’s shelf life. User determines suitability of product for intended use and assumes all risks. User’s and/or buyer’s sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.**

Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/group/SikaCorp/termsandconditions.html> or by calling 1-800-933-7452.

Sika Corporation
201 Polito Avenue
Lyndhurst, NJ 07071
Phone: +1-800-933-7452
Fax: +1-201-933-6225
usa.sika.com

Sika Mexicana S.A. de C.V.
Carretera Libre Celaya Km. 8.5
Fracc. Industrial Balvanera
Corregidora, Queretaro
C.P. 76920
Phone: 52 442 2385800
Fax: 52 442 2250537



Product Data Sheet
SikaFiber®-800 Stealth
November 2020, Version 02.01
021408021000000125

SikaFiber-800Stealth-en-US-(11-2020)-2-1.pdf

